Product Capacity of HDPE plant

GRADES		PROPERTY	MFR (190°C/2.16 kg)	Density
		UNIT	(g/10 min).	g/l
		ASTM METHOD	D 1238	ISO 1183
		INTERNAL METHOD	17066	
6. CABLE				
HF 4750 K	cable insulation		3.5±0.5	0.946±0.002
7. PIPE(NATURAL/COLOR)				
Available > HM 5010 T2 N	pressure pipes, e.g. drinking-water and gas pipes,waste pipes and sewer pipes,their fittings and also sheets(UV stabilization and pigments during processing)		0.45±0.06	0.945±0.002
HM 5010 T3 N	high-quality PE 80 pressure pipes for gas and water transportation(UV stabilization and pigments during processing)		0.43±0.03	0.944±0.002
HM 5010 T3 Black	high-quality PE 80 pressure pipes for gas and water transportation(UV stabilization and pigments during processing)		0.43±0.03	0.954±0.002
Available > HM CRP 100 N	top quality PE 100 pressure pipes for gas and water transportation at higher pressures or with thinner walls as PE 80 (UV stabilization and/or pigments during precessing)		0.22±0.03	0.948±0.002
Available > HM CRP 100 Black	top quality PE 100 pressure pipes for gas and water transportation at higher pressures or with thinner walls as PE 80 (UV stabilization and/or pigments during precessing)		0.22±0.02	0.957±0.002
HM CRP 100 Blue	top quality PE 100 pressure pipes for gas and water transportation at higher pressures or with thinner walls as PE 80 (UV stabilization and/or pigments during precessing)		0.22±0.02	0.948±0.002
HM CRP 100 O/Y	top quality PE 100 pressure pipes for gas and water transportation at higher pressures or with thinner walls as PE 80 (UV stabilization and/or pigments during precessing)		0.22±0.02	0.949±0.002
8. FILM				
HM 9455 F	for blown films with paperlike quality,suitable for counter bags,carrier bags and wrapping films,excellent processing		0.28±0.05	0.956±0.002
Available > HM 9450 F	for blown films with paperlike quality,suitable for counter bags,carrier bags and wrapping films,excellent processing		0.28±0.05	0.949±0.002
HM 9450 F1	for blown films with paperlike quality,suitable for counter bags,carrier bags and wrapping films,excellent processing and sealability		0.22±0.05	0.950±0.002
HM 9455 F1	for blown films with paperlike quality,suitable for counter bags,carrier bags and wrapping films,excellent processing		0.22±0.05	0.957±0.002
HM 9445 HT	for blown films with paperlike quality,suitable for counter bags,carrier bags and wrapping films,excellent processing		0.18±0.03	0.944±0.002